

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>5</sup> :</b> <b>C08G 63/88</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 94/28047</b> <b>(43) International Publication Date:</b> 8 December 1994 (08.12.94)
<b>(21) International Application Number:</b> PCT/GB94/01181 <b>(22) International Filing Date:</b> 1 June 1994 (01.06.94)  <b>(30) Priority Data:</b> 9311402.3 2 June 1993 (02.06.93) GB  <b>(71) Applicant (for all designated States except US):</b> ZENECA LIMITED [GB/GB]; 15 Stanhope Gate, London W1Y 6LN (GB).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> LIGGAT, John, Jamieson [GB/GB]; 64 Briggs Avenue, Middlesbrough, Cleveland TS6 6XN (GB). O'BRIEN, Gregory [US/US]; 7 Beechwood Circle, Hockessin, DE 19707 (US).  <b>(74) Agents:</b> MANNION, Sally, Kim et al.; Group Patents Services Dept., P.O. Box 6, Shire Park, Bessemer Road, Welwyn Garden City, Hertfordshire AL7 1HD (GB).		<b>(81) Designated States:</b> AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, ES, FI, GB, GE, HU, JP, KG, KP, KR, KZ, LK, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> With international search report.
<b>(54) Title:</b> PROCESSING OF POLYESTERS  <b>(57) Abstract</b>  Method of retarding age embrittlement of polyester comprising heat treating the polyester after preparation by cooling below 90 °C and then heating at 90 °C to 160 °C within 24 hours of preparation, and a polyester composition in which ageing is substantially retarded compared to the non-heat treated polyester. The invention encompasses the polyester composition which has been subjected to the method.		

*FOR THE PURPOSES OF INFORMATION ONLY*

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

**PROCESSING OF POLYESTERS**

THIS INVENTION relates to processing of polyesters and in particular to producing shaped articles less liable to embrittlement.

It has been disclosed by de Koning et al in Polymer 92, 33, (15), 3295-3297 that whereas one such polyester poly(R)-3-hydroxybutyrate when freshly moulded shows ductile behaviour, within several weeks at room temperature the tensile modulus doubles and elongation at break drops below 10%. A typical feature of such ageing is that it can be partly reversed by heat or mechanical strain. Using mild 'deageing' treatment, the improvement in ductility is only small and temporary, but heating at above 100°C restores the original mechanical properties and prevents or at least retards ageing to a large extent.

It has now been found that such age-embrittlement can be prevented or slowed by applying the heat treatment to shaped articles made substantially of polyhydroxybutyrate (PHB), polyhydroxybutyrate-co-valerate (PHBV) and/or other polyhydroxyalkanoates before they have undergone significant ageing.

Thus according to the invention there is provided a polyester composition comprising polyhydroxyalkanoate (PHA) in which ageing of the polyester is retarded characterised in that after preparation the polyester is cooled to below 90°C and then heat treated at 90°C to 160°C within 24 hours of preparation, and in that subsequent ageing is substantially retarded compared to the non-heat treated polyester.

In a further aspect of the invention there is provided a shaped article at least partly made of polyhydroxyalkanoate (PHA) in which ageing of the polyester is substantially retarded characterised in that after preparation the article is allowed to cool to below 90°C is heat treated at 90°C to 160°C within 24 hours of preparation, and in that subsequent ageing is substantially retarded compared to the non-heat treated polyester.

"Ageing" means deterioration of the mechanical properties of polymer with time, for example, ductility and tensile strength. Loss of mechanical properties can be measured by measurements indicative of ageing, for example, elongation to break and impact resistance (Izod).

In the present context "substantially retarded" means that for

practical purposes the polyester or article is not defective for brittleness or ductility for at least one month after the heat treatment. Preferably the polyester or article shows at least 40%, especially 60%, improvement in brittleness or ductility compared to the non-heat treated polyester or article. This can be measured using any measurement indicative of ageing, for example, by elongation to break measurements or impact strength measurements (Izod).

By "within 24 hours" is meant up to 24 hours, preferably within 12 hours of preparation, particularly 60 minutes or less from preparation.

"At least partly made" means having structural components made of PHA, for example PHB or PHBV, to such an extent that embrittlement of the PHA components embrittles the whole article. Thus for example articles having PHB components linked to other components, and articles made of a matrix of some other polymer with PHB inclusions, are within the invention. Articles made of PHB alone benefit most from the invention.

The heat treatment can be any that does not involve a step effecting substantial crystallisation of the polyester in the article presented to the heat treatment at 100°C to 140°C.

If shaping has been by melting or sintering, the heat treatment may follow immediately upon shaping, for example by holding an article in its mould for a suitable time; the mould temperature may be deliberately adjusted or may be arrived at as the resultant of the molten polymer temperature and the initial mould temperature. If desired, the article may be held at a temperature appropriate for crystallisation before the heat treatment according to the invention. If shaping has been continuous, for example by extrusion of fibre or film or a profile, the heat treatment can be effected in a zone downstream of the extruder and any quench, crystallisation or draw zone.

The PHA is especially capable of a relatively high level of crystallinity, for example over 30%, especially 50-90%, in the absence of plasticiser. Suitably it is or includes at least one microbiologically produced polyester having units of formula I:



where m is in the range 1-13 and n is 2m or (if m is at least 2) 2m-2.

Typically  $C_m H_n$  contains 2-5 carbon atoms in the polymer chain and the remainder (if any) in a side chain. In very suitable polyesters  $m$  is 3 or 4,  $n$  is  $2m$  and especially there are units with  $m = 3$  and  $m = 4$  copolymerised together and with respectively a  $C_1$  and  $C_2$  side chain on the carbon next to oxygen in the chain. Particular polyesters contain a preponderance of  $m = 3$  units, especially homopolymer (PHB) or with at least 70 mol %, preferably 70-98% of such units, the balance (if any) being units in which  $m = 4$  (PHBV). The molecular weight of the PHA is preferably over 50000, especially over 100000, up to eg  $2 \times 10^6$ .

The PHA is conveniently a blend of two or more polymers or copolymers differing in the value of  $m$ . A particular example contains

- (a) PHA consisting essentially of Formula I units in which 2-5 mol % of units have  $m = 4$ , the rest  $m = 3$ ; and
- (b) PHA consisting essentially of Formula I units in which 5-30 mol % of units have  $m = 4$ , the rest  $m = 3$ .

In each such PHA there are side chains as above mentioned. The proportions in such a blend are preferably such as give an average  $m = 4$  content in the range 4 - 20 mol %.

In each such PHA having units with  $m = 3$  and/or  $m = 4$  there may be very small, typically fractional, percentages of units having higher values of  $m$ .

Typically the composition contains microbiologically produced PHA to the extent of over 50% w/w, especially over 80% w/w.

PHA comprising hydroxybutyrate units and hydroxyvalerate units includes PHBV copolymers containing up to 1 mol percent of other oxyalkanoate units whether introduced deliberately or not.

The polyhydroxyalkanoate is preferably polyhydroxy-butyrate (PHB) or polyhydroxybutyrate-co-valerate (PHBV), which may be 3-hydroxy or 4-hydroxy or a mixture of both. Especially preferred are the (R)-3-hydroxy forms of PHB and PHBV.

The PHA is preferably a fermentation product, especially of a microbiological process in which a microorganism lays down PHA during normal growth or is caused to do so by cultivation in the absence of one or more nutrients necessary for cell multiplication. The microorganism may be wild or mutated or may have had the necessary genetic material

introduced into it. Alternatively the necessary genetic material may be harboured by a eukaryote, to effect the microbiological process.

Examples of suitable microbiological processes are the following:  
for Formula I material with  $m = 3$  or  $m =$  partly 3, partly 4 :

- 5 in EP-A-69497 (Alcaligenes eutrophus);  
for Formula I material with  $m = 3$ : US 4101533 (A. eutrophus H-16), EP-A-144017 (A. latus);  
for Formula I material with  $m = 7-13$ : EP-A-0392687 (various Pseudomonas).

- 10 The PHA can be extracted from the fermentation product cells by means of an organic solvent, or the cellular protein material may be decomposed leaving microscopic granules of PHA. For specialised end uses the cellular protein may be partly or wholly allowed to remain with the PHA, but preferably subjected to cell breakage.

- 15 Alternately if the PHA can be a product of synthetic chemistry using processes known in the art. PHB can be prepared according to Bloembergen, S. and Holden, D. A., Macromolecules. 1989, Vol 22, p1656-1663). PHBV can be prepared according to Bloembergen, Holden, Bluhm, Hamer and Marchessault, Macromolecules. 1989, Vol 22, p1663-  
20 1669.

- The properties of the polyester or article of the present invention can be assessed using the following measurements : stress-strain curve including calculations of elongation to break, Youngs modulus, and tensile strength; impact testing, for example Izod; and dynamic  
25 mechanical thermal analysis (DMTA). These are all standard methods for testing mechanical properties.

If the PHA contains  $m = 3$  units and then 1, especially more than 5, mol percent of units in which  $m = 4$  or greater than 6, the composition subjected to shaping preferably contains a plasticiser.

- 30 The polyester composition can contain the usual polymer processing additives such as plasticisers, particulate or fibrous or platy filler or reinforcer, fibres, nucleating agents (for example boron nitride, talc or ammonium chloride), and pigments. The nucleant is preferably present in 0.1 to 10phr (parts per hundred), especially 1 to 5phr. The  
35 composition can be in the form of mouldings, extrudates, coatings, films

or fibres, including multilayer coatings, films or fibres.

The plasticiser is any material capable of plasticising polyester, i.e. capable of improving the ductility of the polyester and specially any material capable of plasticising PHB or PHBV. There may be one or more plasticisers present. For the ratio of plasticiser to PHA the range up to and including 40 phr w/w, preferably 1 to 40 phr w/w includes most of the likely uses and for making effectively rigid but not brittle articles the range 5-20 especially 6-12, phr w/w is generally suitable.

Examples of suitable plasticisers are

- 10 (a) high-boiling esters of polybasic acids, such as phthalates, isophthalates, citrates, fumarates, glutamate, phosphates or phosphites. The esterified radicals may be for example C<sub>1</sub> - C<sub>12</sub> alkyl, aryl, aralkyl or aralkyl. Particular examples are dioctyl-, dibutyl- and dodecyl- phthalates and dialkylalkylene oxide glutamate (Plasthall 7050);
- 15 (b) high boiling esters and part- of polyhydric alcohols, especially glycols, polyglycols and glycerol. The acid-derived radical of the ester typically contains 2-10 carbon atoms. Examples are triacetin, diacetin and glyceryl dibenzoate;
- 20 (c) aromatic sulphonamides such as paratoluene sulphonamide.

A particularly preferred plasticiser is a doubly esterified hydroxycarboxylic acid having at least 3 ester groups in its molecule.

- "Doubly esterified" means that at least some of the hydroxy groups of the hydroxycarboxylic acid are esterified with a carboxylic acid and at least some of the carboxy groups thereof are esterified with an alcohol or phenol. Preferably at least the hydroxycarboxylic acid from which the ester is derived is aliphatic or cycloaliphatic. Its backbone structure (that is, apart from carboxy groups) preferably contains 2-6 carbon atoms. It contains preferably 2-4 carboxy groups and 1-3 hydroxy groups; and preferably the number of carboxy groups exceeds the number of hydroxy groups.

- The groups with which the carboxy groups are esterified contain preferably 1-7, especially 2-5 carbon atoms. In the ester molecule they can be the same or different. Preferably they are aliphatic. For thermal stability but biodegradability such aliphatic groups preferably have

straight chains. If desired, a small portion of these groups are divalent, so as to give an oligomer suitably containing up to 3 repeating units.

5 The groups with which the hydroxy groups are esterified preferably contain 2-7, especially up to 4, carbon atoms, including the carbon atom of the carboxy of such groups. In the ester molecule such groups can be the same or different. Preferably they are aliphatic and, for thermal stability and biodegradability, have straight chains. If desired, a small proportion of these groups are divalent, so as to give an oligomer suitably containing up to 3 repeating units. An example of such a plasticiser is Estaflex<sup>\*</sup> ATC. \* indicates a tradename or registered trademark.

10 This list is not exhaustive and any plasticiser of polyester which is not listed above or which becomes available after the date of this application would be suitable for use in this invention.

15 The process used to shape the article can be for example any one of injection moulding, compression moulding, extrusion of fibre or films, extrusion of profile, gas-current spinning, tack spinning, coating melt onto substrate, coating latex onto substrate, shaping solution in volatile solvent.

20 The invention also provides a method of retarding age embrittlement of polyester comprising heat treating said polyester characterised in that after preparation the polyester is cooled to below 90°C and then heat treated at 90°C to 160°C within 24 hours of preparation.

25 The heat treatment is more preferably in the range 90 to 150°C, especially 100°C to 140°C.

The heating time is typically at least a few seconds, preferably from 5 seconds to 20 hours, especially 0.5 minutes to 14 hours, particularly 0.5 minutes to 2 hours.

30 The heating time required for optimal effect is dependent on the heating temperature, i.e. the higher the temperature the less time that is required to achieve optimal effect. Also the temperature can be chosen to suit the characteristics of the processing plant and economic requirements.

35 Heating can be effected in air or oxygen-depleted or inert gas or in



vacuo, or in water or a fluid which does not interfere with the integrity of the polyester, or in a mould. Heat transfer can be by conduction, radiation, convection or resistive heating. Heat transfer methods may include ovens, water baths and hot rollers. A preferred form of heat transfer is by infra red radiation, for example, black body and quartz tubes. The shaped article is generally subjected to infra red radiation for 30 seconds to 15 minutes, preferably 30 seconds to 10 minutes.

The shaped articles may be run through the oven or other heating method on a continuous belt at a speed which is optimal to enable the shaped article to reach the correct temperature. A preferred method is to have a multi-zone system, preferably a 2 zone heat system in which the first zone gives a rapid rate of heating (i.e. the actual temperature in the zone may be higher than that to be achieved by the shaped article) to bring it to the actual temperature required and then in the second zone the shaped article is maintained at the actual temperature to be achieved for the desired time period.

The invention provides methods of making the composition by mixing its components. If desired, this may be effected in a solvent, such as a halogenated hydrocarbon or alkylene carbonate. Such a method is convenient for coating or for centrifugal spinning of fibres. More conveniently, if a plasticiser is present, the plasticiser is mixed with powdered dry polymer and the mixture is treated in conditions of shear, such as in a plastic mill or extruder. The product is then granulated and used as feed for a shaping operation such as extrusion, injection moulding, injection blow-moulding or compression moulding.

The composition is especially useful for making the following shaped articles: films, especially for packaging, fibres, non-woven fabrics, extruded nets, personal hygiene products, bottles and drinking vessels, agricultural and horticultural films and vessels, ostomy bags, coated products (such as paper, paperboard, non-woven fabrics), agricultural and horticultural films and vessels, slow-release devices. Alternatively, the polymer composition with suitable additives can be used as an adhesive.

The invention is now further described, but is not limited by, the following examples.

#### Formulation and test procedures

In the following examples, the PHB and PHBV polymers were the [R]-3-hydroxy form. Compositions were prepared by mixing copolymer (500g) with 1 phr boron nitride and (if required) plasticiser, and extruding the mixture in a Betol 2520 extruder in these conditions:

5	Zone 1	130°C
	Zone 2	140°C
	Zone 3	150°C
	Die	150°C
	Screw Speed	100 rpm

10 The extrudate, a single 4mm lace, was crystallised at 50 - 60°C in a water bath, dried in a current of air and cut into granules.

Granules were then injection moulded (Boy 15S) into hot moulds, to give dumbbell-shaped tensile bars according to ISO R 537/2, their prismatic part measuring 40 x 5 x 2 mm. The mould temperature was held at 60°C after entry of the polymer. The bars were numbered as they came out of the mould, then allowed to cool at ambient temperature.

Injection moulding conditions were:-

	Barrel Zone 1	130°C
20	Barrel Zone 2	130°C
	Nozzle	130°C
	Mould heater temperature	74-77°C
	Mould temperature	60°C
	Pressure hold on time	12 sec
25	Cooling time	30 sec
	Injection pressure	45 bar
	Screw Feed	250 rpm

After removal from the mould the bars were stored for various periods at ambient temperature and then subjected to tensile testing using an Instron 1122 fitted with a Nene data analysis system. The jaw separation used was 50mm and crosshead speed was 10mm/min<sup>-1</sup>.

#### Example 1

The composition PHB 10V and 1 phr boron nitride + 10 phr dioctylphthalate (Jayflex DIOP) (RTM) was prepared and moulded as described. The bars were removed from the mould. The bars were then

heat treated at 110°C for 1 hour. The bars were tested for elongation to break over various periods. The lower the elongation to break the less ductile the polymer. Results are shown in Table 1 as percentage elongation to break.

5 **Table 1**

	Ageing time after heat treatment(days)				
	0	1	3	7	28
Control	459.3	15.3	-	13.8	12.8
treated	282.5	-	44.8	30.6	29.0

(-) means not tested.

10 It is evident that for the heat treated polymer the extension to break, although initially considerably less than for the non-heat treated polymer, decreases less rapidly over a period of time to a level significantly (over 100%) and usefully higher than that of the untreated polymer.

15 **Example 2**

The experiment of Example 1 was repeated using plasticised homopolymer (1 phr BN as nucleant and 20 phr Diolpate PPA 350 as plasticiser).

20 The bars were released directly after moulding. Within 30 seconds of demoulding the bars were heat treated at 110°C for 1 minute. The bars were tested for extension to break and the values are represented as percentage extension to break.

**Table 2**

	Ageing time after treatment (days)					
	0	1	7	28	84	185
Control	619	340	21.2	17.4	14.9	11.95
treated	540	427	103	34.9	25.8	21.9

25 It is evident that the extension to break for the heat treated polymer, although starting from a lower value, does not decrease as rapidly as the

non-heat treated polymer and is still significantly higher (approximately 100%) than the corresponding value for the non-heat treated polymer at 6 months after treatment.

### Example 3

5 The experiment of Example 1 was repeated using plasticised homopolymer (1 phr BN as nucleant and 20 phr Reoplas 39 as plasticiser).

The bars were released directly after moulding. Within 30 minutes after moulding the bars were heat treated at 140°C for 30 minutes. The bars  
10 were tested for extension to break and the values are represented as percentage extension to break.

Table 3

	Ageing time after treatment (days)				
	0	●	7	28	84
Control	55.2	20.5	10.5	7.4	6.3
15 Treated	49.7	42	42.9	30.2	-

These results also demonstrate that at 28 days after treatment the heat treated polymer is significantly more ductile than the non-heat treated polymer.

## CLAIMS

1. Polyester composition comprising polyhydroxyalkanoate (PHA) in which ageing of the polyester is retarded characterised in that after preparation the polyester is cooled to below 90°C and then heat treated at 90°C to 160°C within 24 hours of preparation, and in that subsequent ageing is substantially retarded compared to a non-heat treated polyester.
2. Polyester composition according to claim 1 wherein the composition contains a plasticiser.
3. Polyester composition according to claim 2 wherein the composition contains up to and including 40 phr w/w of plasticiser.
4. Polyester composition according to claim 1 which consists essentially of polyhydroxyalkanoate (PHA).
5. Polyester composition according to any of the previous claims wherein the composition is heat treated at 100°C to 140°C.
6. Polyester composition according to any of the previous claims wherein the composition shows at least 40% improvement in brittleness or ductility compared to the non-heat treated polyester composition.
7. Polyester composition according to any of the previous claims wherein the polyhydroxyalkanoate is either polyhydroxybutyrate or polyhydroxybutyrate-co-valerate.
8. Polyester composition according to Claim 7 wherein the polyhydroxybutyrate is poly-(R)-3-hydroxybutyrate and the polyhydroxybutyrate-co-valerate is poly-(R)-3-hydroxybutyrate-co-(R)-3-hydroxyvalerate.
9. Shaped article at least partly made of polyhydroxy-alkanoate (PHA) in which ageing of the polyester is retarded characterised in that after preparation the article is allowed to cool to below 90°C is heat treated at 90°C to 160°C within 24 hours of preparation, and in that subsequent ageing of the polyester is substantially retarded compared to a non-heat treated polyester.
10. Method of retarding age embrittlement of polyester comprising heat treating said polyester characterised in that after preparation

the polyester is cooled to below 90°C and then heat treated at 90°C to 160°C within 24 hours of preparation.

11. Method according to Claim 10 wherein the polyester is heat treated for a period from 5 seconds to 20 hours.
12. Method according Claims 10 or 11 wherein the polyester is heat treated at 100°C to 140°C.
13. Method according to any of Claims 10 to 12 wherein the heat transfer is by conduction or radiation.
14. Method according to Claim 13 wherein the heat transfer is by infra red radiation.
15. Method according to any of Claims 10 to 14 wherein the polyester is heat treated immediately following shaping of the polyester into an article.
16. Method according to any of Claims 10 to 15 wherein the polyester comprises polyhydroxyalkanoate.
17. Method according to any of Claims 10 to 16 wherein the polyester comprises polyhydroxy-butyrates or polyhydroxybutyrate-co-valerate.
18. Method according to any of Claims 10 to 17 wherein the polyester contains a plasticiser.

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 94/01181

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 5 C08G63/88

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 C08G C08J C12P C08L C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	POLYMER vol. 33, no. 15, 1992, OXFORD pages 3295 - 3297 G. J. M. DE KONING ET AL 'Ageing phenomena in bacterial poly[(R)-3-hydroxybutyrate]' cited in the application	1,4-18
Y	see page 3295, introduction ---	2,3
Y	WO,A,92 01548 (E.I. DU PONT DE NEMOURS AND CO) 6 February 1992 see claims 1-9 --- -/-	2,3

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

\*A\* document defining the general state of the art which is not considered to be of particular relevance

\*E\* earlier document but published on or after the international filing date

\*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\* document referring to an oral disclosure, use, exhibition or other means

\*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*&amp;\* document member of the same patent family

Date of the actual completion of the international search

29 August 1994

Date of mailing of the international search report

05. 09. 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3016

Authorized officer

Decocker, L

## INTERNATIONAL SEARCH REPORT

Intern. Application No

PCT/GB 94/01181

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	CHEMICAL ABSTRACTS, vol. 105, no. 14, 6 October 1986, Columbus, Ohio, US; abstract no. 116100, SAIKI, NORITSUGU ET AL 'Stretching of poly(beta-hydroxybutyric acid) molding' see abstract & JP,A,61 069 431 (TEIJIN LTD.) 10 April 1986 ---	1-18
P,X	POLYMER vol. 34, no. 19 , 1993 , OXFORD pages 4089 - 4094 G. J. M. DE KONING AND P. J. LEMSTRA 'Crystallization phenomena in bacterial poly[(R)-3-hydroxybutyrate]: 2. Embrittlement and rejuvenation' see the whole document ---	1,4-18
A	GB,A,2 160 208 (ICI) 18 December 1985 see claims 1-7 -----	1



# INTERNATIONAL SEARCH REPORT

Information on patent family members

Inter. Appl. Application No

PCT/GB 94/01181

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9201548	06-02-92	US-A- 5076983 AU-A- 8289691 EP-A- 0544701	31-12-91 18-02-92 09-06-93
JP-A-61069431	10-04-86	JP-C- 1638194 JP-B- 2063056	31-01-92 27-12-90
GB-A-2160208	18-12-85	NONE	

